

## THE NOISE REDUCING INSULATION FOR CAST IRON WASTE WATER PIPES



- Improved acoustic comfort
- Easy application over flanges and elbows
- < 15db(A) on cast iron pipes

## Technical Data - Tubolit AR Fonoblok

Brief description Flexible, closed-cell extruded insulation material to reduce noise and prevent condensation especially on cast iron pipes for waste water, rain water and sewage pipes.

Foam material based on polyethylene. Factory made polyethylene foam (PEF) according to EN 14313. Material type

Colour blue

Material Special Information

Self-adhesive coating on tapes: pressure-sensitive adhesive coating on modified acrylate basis with mesh structure, covered with polyethylene foil.

Acoustical and thermal insulation of internal waste water, rain water and sewage pipes in residential and non-residential buildings. For complex and large diameter rain collecting and (roof-) drainage pipes, to provide optimal protection against the risk of condensation, we recommend using Armaflex insulation. Applications

EC Certificate of Constancy of Performance no. 0551 and 0543 (tape) of Güteschutzgemeinschaft Hartschaum (GSH) e.V., Celle Remarks

Property	Value/Assessment	Test*1	Super- vision*2	Special Remark			
Temperature Range							
Temperature Range	max. service temperature + 100 °C	(+ 85 °C for tapes)	EU 5677	○/●	Tested acc. to EN 14707 and EN 14313		
	min. service temperature	(as is usual in plumbing installations)					
Thermal Conductivity							
Thermal Conductivity <sup>1</sup>	ϑ <sub>m</sub> 40 [°C]	λ=	EU 5677	∘/•	Declared acc. to EN ISO 13787 Tested acc. to EN ISO 8497		
	Tubolit $\lambda \leq 0.045$ W/(m·K) AR Fonoblok	$[41 + 0.1 \cdot \vartheta_{m} + 0.0008 \cdot (\vartheta_{m}-40)^{2}]/1000$					
	Tubolit $\lambda \leq 0.045$ W/(m·K) AR tape	$[41 + 0.1 \cdot \vartheta_{\rm m} + 0.0008 \cdot (\vartheta_{\rm m}-40)^2]/1000$					
Fire performance							
Reaction to fire <sup>2</sup>	Tubolit AR Fonoblok E		EU 5677	0/●	Classified acc. to EN 13501-1 Tested acc. to		
	Tubolit AR tape E				EN ISO 11925-2		
Acoustic Performance							
Reduction of structure-borne sound transmission	on cast-iron waste water pipes ≤ 15 dB(A)				Tested acc. to EN 14366		
Other technical features							
Dimensions and tolerances	In accordance with EN 14313, table 1 and 2			0	Tested acc. to EN 822 EN 823 EN 13467		
Storage & Shelf life	Tapes self-adhesive: 1 year				Can be stored in dry, clean rooms at normal relative humidity (50% to 70%) and ambient temperature (0 °C – 35 °C).		

<sup>1.</sup> Due to testing method and laboratory equipment, thermal conductivity is measured for Tubolit DG, S and DHS in a regular way

All data and technical information are based on results achieved under typical application conditions. Recipients of this information should, in their own interest and responsibility, clarify with us in due time whether or not the data and information apply to the intended application area. During storage of the product blooming on the surfaces may occur, especially at wall thickness below 19mm. This blooming does not affect the technical properties of the material, but can affect the adhesion properties. Therefore, the surface needs to be cleaned (wiped off) before adhesives can be applied.

<sup>2.</sup> The reaction to fire classification is valid on metal surfaces.

<sup>\*1</sup> Further documents such as test certificates, approvals and the like can be requested using the registration number given.

<sup>\*2 •:</sup> Official supervision by independent institutes and /or test authorities o: Own in-factory quality monitoring

## **Tubolit AR Fonoblok tubes endless**



Length 15,0 m, Thickness 5,0 mm, Color blue

Pipe max. Outside-Ø [mm]	5,0 mm insulation thickness						
	Outer- Ø [mm]	Nominal width DN	Code	m/carton	Rolls/carton	€/m	
57	58	50	TL-50/5-AR	135	9	xxx	
64	63	60	TL-60/5-AR	120	8	XXX	
76	78	70	TL-70/5-AR	105	7	xxx	
89	90	90	TL-90/5-AR	75	5	XXX	
108	110	100	TL-100/5-AR	75	5	xxx	
133	135	125	TL-125/5-AR	60	4	XXX	
160	160	150	TL-150/5-AR	45	3	XXX	

## **Tubolit AR Fonoblok tapes self-adhesive**



Color blue, Material from high quality polyethelene

Code	Width [mm]	Length [m]	Thickness [mm]	Rolls/carton	€/roll
TL-TAPE/50-AR	50,0	15	3	12	XXX
TL-TAPE/100-AR ●	100,0	15	3	6	XXX

• Item not in stock. Delivery on request. [MTO]

Armacell GmbH
Robert Bosch Str. 10 • 48153 Muenster • Germany
Phone +49 (0) 251 / 76 03-0 • Fax +49 (0) 251 / 76 03-448
www.armacell.com • info@armacell.com

notes

